

SOLAR GREY

Darker range of the main quarry, **Solar Grey** is characterized by an intense grey background marked by lighter grey veining.

FINISHES AVAILABLE:

Antique | Bush hammered | Honed
Polished | Sandblasted | Diamond Satin
Textured | Waterjet

APPLICATIONS:

Exterior | Interior | Horizontal
Vertical | Commercial | Residential

SANDBLASTED

ANTIQUÉ



PHYSICAL TEST RESULTS

		<i>Imperial</i>	<i>Metric</i>
Absorption by weight	ASTM C97	0.09%	0,09%
Density	ASTM C97	169 lb/ft ³	2.714 kg/m ³
Compressive strength	ASTM C170	9.505 Psi	65,55 Mpa
Modulus of rupture	ASTM C99	1.374 Psi	9,48 Mpa

Computer generated images and printed reproductions may not accurately match natural stone colors.